



## Technical sheet

### EPS 150

### Expanded polystyrene EPS 150

**Use:** thermal insulation of buildings - exterior

Thermo insulating wallboards made from expanded polystyrene beads for buildings, made from raw fireproofed material from the ADEPLAST EPS 150 range; they are used as thermo insulating panels for: spaces with high static load, circulated terraces and underneath floors with medium traffic.



#### Technical data:

Item no.:	<b>EPS 150</b>		
Labeling according to EN 13163+A1:2015:	<b>EPS150-EN 13163-T1-L2-W2-Sb2-P5-BS250-CS(10)150-DS(N)2-DLT(1)5-TR150-WL(T)3</b>		
Reaction to fire	<b>E</b>		SREN 13501-1
Long-lasting water absorption by immersion, (%)	<b>WL(T)3</b>	≤3	SREN 12087
Dangerous substances emission		NPD	SREN 13163
Dynamic rigidity		NPD	SREN 29052-1
Thermal resistance, (m <sup>2</sup> K/W)		0,61 for a thickness of 20mm 1,52 for a thickness of 50mm 3,03 for a thickness of 100mm 4,55 for a thickness of 150mm 6,06 for a thickness of 200mm	SREN 12667
Heat conductivity, (W/Mk)		0.033	SREN 12939
Thickness, (mm)	<b>T1</b>	+/- 1	SREN 823
Water vapor transmission, (Mg/Pa.h.m)		NPD	SREN 12086
Compressive stress at a deformation of 10%, (kPa)	<b>CS(10)150</b>	CS≥150	SREN 826
Determination of deformation under specified load conditions to compression and temperature, (%)	<b>DLT(1)5</b>	≤5	SREN 1605
Tensile strength, (kPa)	<b>BS250</b>	BS≥250	SREN 12089
Stretch resistance perpendicular to the fronts, (kPa)	<b>TR150</b>	TR≥200	SREN 1607
Length, (mm)	<b>L2</b>	1000 +/- 2	SREN 822
Width, (mm)	<b>W2</b>	500 +/- 2	SREN 822
Perpendicularity to length and width, (mm/m)	<b>Sb2</b>	+/- 2	SREN 824
Perpendicularity to thickness, (mm/m)	<b>Sd2</b>	+/- 2	SREN 824
Smoothness, (mm)	<b>P5</b>	+/- 5	
Dimensional stability under normal laboratory conditions, (%)	<b>DS(N)2</b>	+/- 0.2	SREN 1603
Dimensional stability under specified temperature and humidity conditions, (%)	<b>DS(70,90)1</b>	1	SREN 1604

---

Water vapor permeability-  $\delta$ , (mg/(Pa.h.m))

0,009-0,020

SREN 13163  
(table F.2)

---

Storage / Validity: 24 months from date of fabrication on the packaging. Store in dry spaces on wooden pallets, away from direct sunlight exposure, high temperatures and open fire.

---

Technical data are determined under standard conditions, according to SR EN 13163+A1:2015.

---

**Important:**

- During storage and processing, wallboards should not be exposed to direct sunlight, high heat and open fire;
- **Wallboards should not be exposed to fire, aliphatic hydrocarbons, liquid hydrocarbons, acid anhydride, organic solvents and generally corrosive materials or potentially inflammable;**
- This technical sheet replaces all previous versions. Information in this technical sheet represent our experience with this product up to this day. This technical sheet does not clear the user of the product from making his own decision and evaluation including by samples, regarding the appropriateness of using the product. SCHOMBURG / ADEPLAST products as well as their aggregate raw materials are continuously monitored in our own laboratories for consistent quality. Our advisory service is available for questions regarding product application and demonstrations. Comply with the information in the security technical sheet.

Drafted: 15.03.2018